

**IN THE CLAIMS:**

1. (Previously Presented) An isocyanate adduct comprising the reaction product of at least one polyisocyanate, having a functionality  $> 2$ , with compounds having at least two hydrogen atoms which are reactive toward isocyanate groups, the reaction product providing a polymer matrix that is essentially compact, wherein said adduct has a crystalline content of less than 10 j/g determined by differential scanning calorimetry in accordance with DIN 51 004 at 20 K/min from room temperature to 250°C using a nitrogen flow of 3 l/h as carrier gas and an aromatics content reported as carbon atoms in aromatic rings of less than 31% by weight, based on the total weight of the isocyanate adduct, and wherein the compounds having reactive hydrogen atoms comprise at least one polyetherol bi) having a functionality greater than 3 and a molar mass 300 g/mol or greater.
2. (Previously Presented) An isocyanate adduct as claimed in claim 1 which has a thermal conductivity determined by a hot wire method at 23°C of less than 0.2 W/m\*K.
3. (Previously Presented) An isocyanate adduct as claimed in claim 1 further containing fillers.
4. (Previously Presented) An isocyanate adduct as claimed in claim 3, wherein the fillers are hollow microspheres optionally having a pressure loading of greater than 10 bar.
5. (Previously Presented) An isocyanate adduct as claimed in claim 3, wherein the fillers are hollow glass microspheres.
6. (Previously Presented) An isocyanate adduct as claimed in claim 3, wherein the fillers are hollow polymer microspheres.
7. (Previously Presented) An isocyanate adduct as claimed in claim 3, wherein the fillers are hollow ceramic microspheres.

Claims 8-15. (Cancelled)

16. (Previously Presented) An isocyanate adduct as claimed in claim 1 which has a thermal conductivity determined by a hot wire method at 23°C of less than 0.19 W/m\*K.

17. (Previously Presented) An isocyanate adduct as claimed in claim 1, wherein the compounds having reactive hydrogen atoms further comprise at least one polyetherol bii) having a molar mass greater than 1000 g/mol and a functionality of from 1.7 to 3.

18. (Previously Presented) An isocyanate adduct as claimed in claim 17, wherein bi) is used in an amount of from 0.1 to 80 parts by weight and bii) is used in an amount of from 0.1 to 99.9 parts by weight, based in each case on the parts by weight of the compounds having reactive hydrogen atoms.

Claim 19. (Cancelled)